

## KIPP-2 K-PUR Outdoor

### Rubber granulate Lining Paint for Sports outdoor facilities

<b>Type of product:</b>	Polyurethane based 2-component-colour, solvent-reduced, highly abrasion-proof. Highly elastic and light-, weather- and frost-resistant.
<b>Fields of application:</b>	For the lining and sealing of entire sports floors of PUR-bound rubber granulate, EPDM, sprayed layers etc. (round paths). Special rubber subsoils require a proper pre-treatment with special primers (consultation required!)
<b>Preparation of surface:</b>	The floor must be dry and free of dust, grease and oil. Detached granulate parts are to be removed. Lines are to be leveled and lined-out with chalk. Spray 1-2 times (if necessary add max. 3% PUR-thinner V9400).
<b>Mixing Proportions:</b>	Comp. A + B parts by weight 90:10
<b>Preparation time:</b>	Approx. 8 hrs at 20°C
<b>Drying time:</b>	Dry after 1 hour; accessible after 15 hrs., full load-bearing capacity after 4 days
<b>Consumption:</b>	230 – 280g/m <sup>2</sup> and operation
<b>Layer thickness</b>	Approx. 100 -180µm
<b>Packages sizes:</b>	For large consumers (follow mixing proportions) Comp. A: 27 kg; Comp. B: 12 kg For small consumers Comp. A: 4,5 kg; Comp. 0,5 kg
<b>Standard colours available:</b>	yellow app. RAL 1021 Special colours on request! red app. RAL 3000 light-blue app. RAL 5012 white app. RAL 9016 black app. RAL 9017
<b>Storage:</b>	With unopened packages and dry storage: Comp. A at least 18 months Comp. B at least 12 months
<b>Precautionary measures:</b>	During application ensure a constant supply of fresh air at all times. Furthermore all precautionary information, warnings and safety measures can be found on the individual packages. All safety and accident prevention procedures as outlined in respective professional association guidelines are to be observed.

All instructions are the result of our broad experiences and of scientific trials. Because of the varied processing and working conditions these instructions are non-committal.