

# KIPP-2 K-PUR Surface Paint

for sports floors

<b>Type of product:</b>	Polyurethane based 2 component colour, solvent-reduced, highly abrasion-proof and light-resistant
<b>Fields of application:</b>	Excellent adhesive strength on linoleum (Linodur), PVC, PUR, prefinished inlaid floor, unfinished inlaid floor etc.
<b>Preparation of surface:</b>	The floor must be dry and free of dust, grease and oil. Cleaning agents and wax must be completely removed. 2 K-PUR surface paint comp. A + B must be intensively mixed and immediately applied with a lint-free lake colour roll in cross-coat. In order to guarantee the friction coefficient and to facilitate cleaning, the coated surface should be sealed without colour after a 24 hour drying cycle with Sealant 2 K-PUR W or polymer dispersion
<b>Mixing Proportions:</b>	Comp. A + B parts by weight 88 : 12
<b>Preparation time:</b>	Approx. 2 hrs with 20°C
<b>Drying time:</b>	Dry after 2 hrs; full load-bearing capacity after 48 hrs
<b>Consumption:</b>	200 – 250g/m <sup>2</sup>
<b>Layer thickness:</b>	Approx. 100 µm
<b>Pack sizes:</b>	Comp. A: 8,8 or 4,4 kg; Comp. B: 1,2 or 0,6 kg
<b>Available colours:</b>	This product is not on stock. The production takes place again in each case after RAL- tones
<b>Storage ability:</b>	With unopened packs and dry storage: Comp. A 18 months, Comp. B 12 months
<b>Precautionary measures:</b>	During application a constant fresh air supply must be maintained all the times. All precautionary information, warnings and safety measures can be found on the individual packs. All safety and accident prevention procedures as outlined in respective professional association guidelines are to be observed.

All instructions are the result of extensive experiences and scientific experiments. Because of the varied processing conditions, these instructions are non-committal.